

FSE 7340
Fluorosilicone Rubber

Product Description **FSE 7340** is a fluorosilicone rubber, designed for calendaring and moulding for a variety of solvent resistant applications. These products may be used with different peroxides and fillers to develop wide-ranging property profiles. This high tear resistant material is successfully used in a variety of automotive and aerospace applications, where a combination of excellent fluid-resistance with good overall mechanical properties, low-temperature performance and high tear resistance is required.

Key Performance Properties

- Excellent handling
- Blendable
- Easy pigmentable
- Broad fluid resistance
- High tear resistance
- Low temperature flexibility
- Suitable for high temperature applications
- Constant physical properties over wide temperature range

Typical Product Data

Typical Properties of the Uncured Base Compound:			
Appearance			Pale yellow
Density	DIN 53 479 A	g/cm ³	1.43
Typical Properties of the Vulcanized Rubber:			
100 phr FSE 7340 with 1.5 phr 2,5 Dimethyl-2,5 Di(t-butyl peroxy)Hexane (50%) Vulcanization conditions: 15 min. @ 177°C post cured: 4h @ 204°C in hot air			
Hardness	DIN 53 505*	Shore A	42
Tensile strength	DIN 53 504 S2*	N/mm ²	11.2
Elongation at break	DIN 53 504 S2*	%	500
Tear strength	ASTM D 624 die B	N/mm	42
Compression set (22 h @ 177°C)	DIN 53 517*	%	8

*The quoted test methods are corresponding to ASTM standards.

Specifications Typical Product Data should not be used as specifications. For assistance and specifications please contact Momentive performance materials.

Packaging **FSE 7340** is available in 22, 7 kg and 454 kg boxes.

- Instructions for Use** Various organic peroxides will vulcanize **FSE 7340** fluorosilicone compounds. Fabricators should make their selection of curing agents on the basis of method of fabrication, desired properties, and safety considerations. They are mixed into the rubber, if necessary together with **Silopren[®] HV Additives**. The optimum cure cycle will depend on the method of processing used and the physical dimensions of the vulcanized product. Specific applications will require the use of air oven post cures.
- Handling and Safety** Material Safety Data Sheets are available upon request from Momentive performance materials. Similar information for other chemicals used with Momentive performance materials products may be obtained from the respective suppliers.
- Storage Period** The warranty period of **FSE 7340** is 8 months if stored in the original unopened boxes and stored at dry conditions at room temperature (max. 43°C). The storage warranty period begins on the date of shipment.
- Availability** **FSE 7340** products may be ordered from your regular sales contact or please call Momentive performance materials, Bergen-op-Zoom / The Netherlands at 00800-4321-1000 to find out which is the nearest sales office to you.



PRINCIPAL LOCATIONS – Regional Information

North America	World Headquarters 187 Danbury Road Wilton, CT 06897, USA	T 800.295.2392	F 607.754.7517
Latin America	Rodovia Eng. Constâncio Cintra, Km 78,5 Itatiba, SP – 13255-700, Brazil	T +55.11.4534.9650	F +55.11.4534.9660
Europe, Middle East, Africa and India	D-51368 Leverkusen Germany	T 00.800.4321.1000 T +31.164.293.276	F +31.164.241.750
Pacific	Akasaka Park Building - 5-2-20 Akasaka Minato-ku, Tokyo 107-6112 Japan	T +81.3.5544.3100	F +81.3.5544.3101

CUSTOMER SERVICE CENTERS

North America	Charleston, WV 25314, USA E cs-na.silicones@momentive.com		
	<ul style="list-style-type: none"> • Specialty Fluids • UA, Silanes, Resins, and Specialties • RTV Products-Elastomers • Sealants and Adhesives & Construction 	T 800.523.5862 T 800.334.4674 T 800.332.3390 T 877.943.7325	F 304.746.1654 F 304.746.1623 F 304.746.1623 F 304.746.1654
Latin America	E cs-la.silicones@momentive.com		
	<ul style="list-style-type: none"> • Argentina & Chile • Brazil • Mexico & Central America • Venezuela, Ecuador, Peru, Colombia, & Caribbean 	T +54.11.4862.9544 T +55.11.4534.9650 T +52.55.5899.5135 T +58.212.285.2149	F +54.11.4862.9544 F +55.11.4534.9660 F +52.55.5899.5138 F +58.212.285.2149
Europe, Middle East, Africa and India	E cs-eur.silicones@momentive.com	T 00.800.4321.1000 T +31.164.293.276	F +31.164.241750
Pacific	E cs-ap.silicones@momentive.com		
	<ul style="list-style-type: none"> • Japan • China • Korea • Singapore 	T +81.276.20.6182 T +86.21.5050.4666 (ext. 1523) T +82.2.6201.4600 T +65.6220.7022	
Worldwide Hotline	Worldwide Web www.momentive.com	T 800.295.2392 T +607.786.8131	F +607.786.8309

DISCLAIMER: THE MATERIALS, PRODUCTS AND SERVICES OF MOMENTIVE PERFORMANCE MATERIALS INC., MOMENTIVE PERFORMANCE MATERIALS USA INC., MOMENTIVE PERFORMANCE MATERIALS ASIA PACIFIC PTE. LTD., MOMENTIVE PERFORMANCE MATERIALS WORLDWIDE INC., MOMENTIVE PERFORMANCE MATERIALS Gmbh & Co. KG, MOMENTIVE PERFORMANCE MATERIALS SUISSE Sarl, THEIR SUBSIDIARIES AND AFFILIATES DOING BUSINESS IN LOCAL JURISDICTIONS (collectively "SUPPLIERS"), ARE SOLD BY THE RESPECTIVE LEGAL ENTITY OF THE SUPPLIER SUBJECT TO SUPPLIERS' STANDARD CONDITIONS OF SALE, WHICH ARE INCLUDED IN THE APPLICABLE DISTRIBUTOR OR OTHER SALES AGREEMENT, PRINTED ON THE BACK OF ORDER ACKNOWLEDGMENTS AND INVOICES, AND AVAILABLE UPON REQUEST. ALTHOUGH ANY INFORMATION, RECOMMENDATIONS, OR ADVICE CONTAINED HEREIN IS GIVEN IN GOOD FAITH, SUPPLIERS MAKE NO WARRANTY OR GUARANTEE, EXPRESS OR IMPLIED, (i) THAT THE RESULTS DESCRIBED HEREIN WILL BE OBTAINED UNDER END-USE CONDITIONS, OR (ii) AS TO THE EFFECTIVENESS OR SAFETY OF ANY DESIGN INCORPORATING SUPPLIERS' PRODUCTS, MATERIALS, SERVICES, RECOMMENDATIONS OR ADVICE. AFOREMENTIONED EXCLUSIONS OR LIMITATION OF LIABILITY ARE NOT APPLICABLE TO THE EXTENT THAT THE END-USE CONDITIONS AND/OR INCORPORATION CONDITIONS CORRESPOND TO THE RECOMMENDED CONDITIONS OF USE AND/OR OF INCORPORATION AS DESCRIBED BY SUPPLIER IN ITS PRODUCT DATA SHEET AND/OR PRODUCT SPECIFICATIONS.

EXCEPT AS PROVIDED IN SUPPLIERS' STANDARD CONDITIONS OF SALE, SUPPLIERS AND THEIR REPRESENTATIVES SHALL IN NO EVENT BE RESPONSIBLE FOR ANY LOSS RESULTING FROM ANY USE OF ITS MATERIALS, PRODUCTS OR SERVICES DESCRIBED HEREIN.

Each user bears full responsibility for making its own determination as to the suitability of Suppliers' materials, services, recommendations, or advice for its own particular use. Each user must identify and perform all tests and analyses necessary to assure that its finished parts incorporating Suppliers' products, materials, or services will be safe and suitable for use under end-use conditions. Nothing in this or any other document, nor any oral recommendation or advice, shall be deemed to alter, vary, supersede, or waive any provision of Suppliers' Standard Conditions of Sale or this Disclaimer, unless any such modification is specifically agreed to in a writing signed by Suppliers. No statement contained herein concerning a possible or suggested use of any material, product, service or design is intended, or should be construed, to grant any license under any patent or other intellectual property right of Suppliers or any of its subsidiaries or affiliates covering such use or design, or as a recommendation for the use of such material, product, service or design in the infringement of any patent or other intellectual property right.